

ENVIROFLEX®

Email: sales@enviroflexpumps.com

The following data is based on tests and believed to be reliable; however, the tabulation should be used as a guide ONLY, since it does not take into consideration all variables, such as elevated temperatures, fluid contamination, concentration, etc. that may be encountered in actual use. All critical applications should be tested. Note: all data based on 21C (70F) unless otherwise noted

<u>TRADE NAME</u>	<u>DESCRIPTION</u>	<u>TRADE NAME</u>	<u>DESCRIPTION</u>
BUTYL	SOBUTYLENE-ISOPRENE	CPE	CHLORINATED POLYETHYLENE
EPDM	ETHYLENE PROPYLENE-DIENE	HYPALON (CSM)	CHLOROSULTONYL POLYETHYLENE
HYTREL	THERMOPLASTIC POLYESTER	NATURAL	NATURAL RUBBER
NEOPRENE	POLYCHLOROPREN	NITRILE	ACRYLONITRILE
NYLON	NYLON POLYMER	SBR	STYRENE-BUTADIENE
SANTOPRENE	ETHYLENE-PROPYLENE-DIENE	TEFLON	FLUOROCARBON RESIN
UHMW	ULTRA-HIGH MOLECULAR WEIGHT POLYETHYLENE	URETHANE	URETHANE
VITON	FLOROELASTOMER	XLPE	CROSS-LINKED POLYETHYLENE

KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

[illegible]

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE
AMINOETHANE		E														
AMINOXYLENE		C														
AMMONIUM CARBONATE (AQ)	E		E			E	E	X	G	E				G	C	
AMMONIUM CHLORIDE (AQ)	E	E	E	E	E	E	E	E	X	E		E	E	E	C	E
AMMONIUM HYDROXIDE	E	E	E	G	C	X	E	X	E	X		E	E	X	C	E
AMMONIUM NITRATE (AQ)	E		E	E			E	E	E	E		E	E	X	C	E
AMMONIUM PHOSPHATE, DIBASIC	E	E	E	E		E	E	E	E	E		E	E		C	E
AMMONIUM SULPHATE (AQ)	E	E	E	E	C	E	E	E	E	E		E	E	E	X	E
AMMONIUM SULPHITE	E	E		E		E				E					E	E
AMMONIUM THIOSULPHATE	E	E		E		E				E		E		G	E	E
AMYL ACETATE	E	C	X	X	C	X	X	X	E	X	X	C	E	X	X	E
AMYL ACETONE	G			X		X				X					X	E
AMYL ALCOHOL	E	E	E	E	E	E	G	X	E	E	X	E	E	X	G	E
AMYL BROMIDE		C														
AMYL CHLORIDE	X	G	X	X		X	X			X		E	E	C	G	G
AMYL ETHER		E														
AMYLAMINE	E	G		F		G				G						
ANETHOLE	X	X		X		X			G	X			G		G	G
ANILINE	E	G	C	X	X	X	X	X	X	X	E	E	E	X	C	E
ANILINE DYES	G	G	G	G		G	G	X	X	G		F	E	X	G	E
ANILINE OIL	G		G	X		X	X	X		X				X	C	
ANIMAL FATS	G	E	C	X	C	X	C	E	E	X	X		E	C	E	E
ANTIMONY PENTACHLORIDE	X			X		X				X						E
AQUA REGIA	X	G	C	C		X	X	X		X		E	X	X	G	X
ARGON	G		E	X	E	X	X	C	E	X		E	E	E		E
ARSENIC ACID	E	E	E	E		E	E	E		E		E		C	E	E
ASPHALT	X		X	X	C	X	X	X	E	X		E	X	G	E	X
ASTM FUEL A	X	E	X	G	E	X	E	E	E	X	X	E	G	E	E	G
ASTM FUEL B	X	G	X	X	E	X	X	E	E	X	X	E	G	E	E	G
ASTM FUEL C	X	G	X	X	E	X	X	G	E	X	X	E	G	X	E	G
ASTM OIL NO. 1	X	E	X	G	E	X	E	E	E	X	X	E	E	E	E	E
ASTM OIL NO. 2	X	E	X	X	E	X	G	E	E	X	X	E	E	E	E	E
ASTM OIL NO. 3	X	G	X	X	C	X	X	E	E	X	X	E	E	E	E	E
ASTM OIL NO. 4	X		X	X		X	X	G		X			E	X	E	E
AUTOMATIC TRANSMISSION FLUID	X	E	X	C		X	G	E		X			E	G	E	E
BANANA OIL	C	G	C					X		X			E			E
BARIUM CHLORIDE (AQ)	E	E	E	E		E	E	E	X	E		E	E	G	E	E
BARIUM HYDROXIDE (AQ)	E	E	E	E	C	E	E	E	E	E		E	E	E	E	E
BARIUM SULFIDE (AQ)	E	E	E	E		E	E	E	F	E		E	E	E	E	E
BEER	E	E	G	E	G	E	G	C	G	E		E	E	X	E	E
BEET SUGAR LIQUORS	E	E	E	E		E	G	E	E	E		E	G	X	E	E
BENZAL CHLORIDE	G	X											E			E
BENZALDEHYDE	E	C	E	X	X	X	X	X	E	X	X	C		X	X	E
BENZENE	X	X	X	X	C	X	X	X	E	X	X	G	G	X	E	E
BENZENE CARBOXYLIC ACID		E														
BENZINE	X		X	X		X	G	E	E	X		E		G	E	E
BENZOIC ACID	X	E	X	X		X	X	X	G	X		G		X	E	E
BENZOL		G	X					X	F			E	G			
BENZOTRICHLORIDE		X											G			G

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE
BENZYL ACETATE	G	G		X		X				X			E		X	E
BENZYL ALCOHOL	X	E	X	F		X	C	X	C	X	X	E	E	X	E	E
BENZYL CHLORIDE	G	X	G	C		C	X	X		C		E	E		C	E
BENZYL ETHER		C														
BIS (2-CLOROETHYL) ETHER		G														
BLACK SULFATE LIQUOR	E		E	G		G	G	G	F	G		E	E	X	E	
BLEACH (2-15%)	G		G	F		X	X	X		X		E	E	X	G	G
BORAX SOLUTION	E	E	E	E	E	G	E	C	E	G	G	E	E	G	E	E
BORIC ACID		E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
BRAKE FLUID (HD-557) 12 DAYS	G	E	E	G			G	C	E	E		E			X	
BRINE	E	E	E	E		E	E	F	C	E		E	E		E	E
BROMACIL			E													
BROMOBENZENE	X	X	X	X		X	X	X		X			C	X	G	C
BROMOCHLOROMETHANE	G	G	G	X		X	X	X		X					X	G
BROMOETHANE		G														
BROMOTOLUENE	X	X		X		X				X					G	F
BUGDIOXANE																E
BUNKER OIL	X		X	X		X	X	E		E		E		G	E	E
BUTADIENE	X		X	C		X	X	X		X		E		X	G	E
BUTANE	E	G	X	G	E	X	E	E	E	X		E	E	E	E	E
BUTANOIC ACID		E														
BUTANOL (BUTYL ALCOHOL)	E	E	G	E	E	E	E	E	E	E	G	E	E	G	E	E
BUTANONE		G			X			X	E		X	G	E	X		E
BUTOXYETHANOL		E														
BUTYL ACETATE	G	G	C	X	C	X	X	X		X		C	E	X	X	E
BUTYL ACRYLATE	X	G	X	X		X	X	X					G		X	G
BUTYL ALCOHOL	E	E	E	E		E	E	E		E		G	E	G	E	E
BUTYL ALDEHYDE	E	G				F							E		X	E
BUTYL BENZYL PHTHALATE	E		E	X		X	X	C		X			E		C	E
BUTYL CARBITOL	E	E	E	C		X	C	X		X		E	E		C	C
BUTYL CELLUSOLVE	E	E	G	X		X	X	C		X		E	E	E	X	E
BUTYL CHLORIDE	F	C		X		X				X			C		G	G
BUTYL ETHER	C	E	C	X		X	X	C		X			E	G	X	E
BUTYL ETHER ACETALDEHYDE	E			X		X				X			E		X	E
BUTYL ETHYL ETHER	G			X		X				X			E			E
BUTYL OLEATE	G		G	X		X	X	X		X					E	
BUTYL PHTHALATE	E	C		X		X				X					F	E
BUTYL STEARATE	X	G	X	X		X	X	G		X		E	E		C	E
BUTYLENE	X		X	X		X	C	G		X				X	E	
BUTYRALDEHYDE	E	G	G	X		X	X	X		X		E	E	X	X	E
BUTYRIC ACID	F	E	G	X	C	F	X	X		X		E	E		G	E
BUTYRIC ANHYDRIDE	F			G		F				X		E			X	E
CADMIUM ACETATE	G	E		X		X				X			E			E
CALCIUM ALUMINATE	E			E		E				E					E	E
CALCIUM BICHROMATE	E			F												G
CALCIUM BISULFIDE			X		G		C	E	F			E				
CALCIUM CHLORIDE	E	E	E	E	E	E	E	E	C	E		E	E	E	E	E
CALCIUM HYDROXIDE	E	E	E	G	E	E	E	E	E	G		E	E	E	E	E
CALCIUM HYPOCHLORITE	G	E	E	F	E	X	X	X	X	X		E	C	X	X	C

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SANTOPRENE	SBR	TEFLON	UHMW	URETHANE	VITON	XLPE
CALCIUM NITRATE	E	E	E	E		E	E	E	E	E		E	E	E	E	E
CALCIUM SULFIDE	E	E	E	E		E	E	G		E		E	E	E	E	E
CALCIUM ACETATE	G	E	E	X		X	G	G		X		E	E	X	X	E
CAPRYLIC ACID	F	E		G		F				X			E			E
CARBAMIDE		E														
CARBITOL	F	E	G	X		X	G	G		X		E	E	X	G	E
CARBOLIC ACID PHENOL	E	E	G	X		X	X	X		X		E	E		E	E
CARBON DIOXIDE	E		C	E	E	E	C	X	E	E		E	E	E	G	E
CARBON DISULFIDE	X	C	X	X		X	X	X	X	X		E	E	X	E	C
CARBON MONOXIDE	E		C	E	E	E	C	E	E	G		E	E	G	E	E
CARBON TETRACHLORIDE	X	X	X	X	C	X	X	X	G	X	X	E	G	X	E	G
CARBONIC ACID	E	E	G	E	X	E	X	X	X	E	X	E		X	E	E
CASTOR OIL	E	E	G	E	G	F	E	E	E	G		E	E	G	E	E
CAUSTIC SODA (SEE SODIUM HYDROXIDE)																
CELLOSOLVE ACETATE	E		G	X		X	X	X	F	X		E	E	X	X	E
CELLUGUARD	E		G	E		E	E	E	E	E		E		X	E	
CETYLIC ACID		E														
CHINA WOOD OIL (TUNG OIL)	C		X	X		X	G	E		X				C	E	
CHLORINATED SOLVENTS	X		X	X		X	X	X	C	X		E		X	E	G
CHLORO-2-PROPANONE		X														
CHLOROACETIC ACID	F		X	X	X	X	X	X	X	X	X	C	E	X	X	E
CHLOROACETONE	G	X	E	X		X	X	X		X		E	E	X	X	E
CHLOROBENZENE	X	X	X	X	X	X	X	X	E	X	X	E	G	X	E	G
CHLOROBUTANE	F	C		X		X				X			G		E	G
CHLORODANE			E					E								
CHLOROETHYL BENZENE	X	X		X		X				X			E		G	E
CHLOROFORM	X	X	X	X	X	X	X	X	X	X	X	E	E	X	E	G
CHLOROPENTANE	X	G		X		X				X			E		E	E
CHLOROSULFONIC ACID	X	X	X	X	X	X	C	X	X	X		C	X	X	X	G
CHLOROTOLUENE	X	X	X	X		X	X	X		X		E	G	X	G	G
CHLOROX	G	E	G	G		X	G	G		X			G	X	E	
CHROME PLATING SOLUTIONS	X		G	X		X	X	X		X			E	X	E	
CHROMIC ACID	F	E	C	G	X	X	X	X	X	X	X	E	E	X	C	G
CHROMIUM TRIOXIDE		E														
CINNAMENE		C														
CIS-9-OCTADECENOIC ACID	G	E		X		X				X					C	E
CITRIC ACID	E		E	E	E	E	E	E	E	E	E	E	E	E	C	E
COAL OIL	X		X	X		X		X	E	X	X		E		E	E
COAL TAR	X		X	X		X	G	E		X			E		E	E
COAL TAR NAPTHA	X			X		X				X					E	E
COCONUT OIL	G		C	X		X	G	E		X		E	E	C	C	E
COKE OVEN GAS	X		X	X		X	X	X	E	X		C		X	E	E
COOLANOL (MONSANTO)			X	G	X	X	E	E		X				X	E	
COPPER CHLORIDE	E	G	E	E	E	F	C	C	C	E		X	E	G	E	E
COPPER CYANIDE	E		E	E		E	E	E		E		E	E	E	E	E
COPPER HYDRATE	E			G		F				G			E		F	E
COPPER HYDROXIDE	E			G		F				G					F	E
COPPER SULFATE	E	E	E	E	E	F	E	E	X	E		E	E	G	E	E
CORN OIL	E	G	C	X	G	X	C	E	G	X		G	E	G	E	E

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SANTOPRENE	SBR	TEFLON	UHMW	URETHANE	VITON	XLPE
COTTONSEED OIL	C	G	C	X	G	X	C	C	E	X		E	E	G	E	C
CREOSOTE	X		X	X		X	C	C	X	X	X	E	E	C	E	E
CRESOLS	X	E	X	X		X	X	X	X	X	X	E	E	X	E	E
CRESYLIC ACID	X		X	X		X	X	X		X		E	E	X	E	E
CROTONALDEHYDE	E	E		X		X				X			E		X	E
CRUDE OIL	X		X	X		X	X	G	E	X		E	E		E	E
CUMENE	X	C	X	X		X	X	X		X		E	E	X	E	E
CUPRIC CARBONATE	E	E		E		F				E			E		E	E
CUPRIC HYDROXIDE		E														
CUPRIC NITRATE	E	E		E		F				E			E	G	E	E
CUPRIC SULFATE	E	E		E		F				E			E	G	E	E
CUTTING OIL	X		X	G		X	G	E		X		E		E	E	
CYCLOHEXANE	X	E	X	X	E	X	X	G	E	X	X	E	E	G	X	E
CYCLOHEXANOL	X	E	X	X		X	G	C	E	X	X	E	E		E	E
CYCLOHEXANONE	X	C	X	X		X	X	X	E	X	X	E	E	X	X	E
CYCLOPENTANE	X	G		X		X				X			E		E	E
CYCLOPENTANOL	X	E		X		X				X			E		G	E
CYCLOPENTANONE	X	G		X		X				X						E
CYCLOPENTYL ALCOHOL		E														
D-FURALDEHYDE		E														
DDT IN KEROSENE	X		X	X		X	F	E	E	X		E			E	E
DECAHYDRONAPHTHALENE		C														
DECAHYDROXYNAPHTHALENE		C														
DECALIN	X	X	X	X		X	X	X		X		E	X		E	E
DECYL ALCOHOL	E	E		E		E				E			E		G	E
DECYL ALDEHYDE	E			X		X				X			E		X	E
DECYL BUTYL PHTHALATE	E			X		X				X			E		F	E
DECYL CARBINOL		E														
DETERGENT, WATER SOLUTION	E	G	E	G		G	G	E		G		E		X	E	
DEVELOPING FLUID (PHOTO)	G		G	E		E	E	E		G					E	
DEXTRON	X		X	X		X	G	E		X				G	E	
DI(2ETHYLHEXYL) ADIPATE		C														
DI(2ETHYLHEXYL) PHTHALATE		C														
DI-ISO-BUTYLENE	X		X	X		X	X	G		X				X	E	E
DI-ISO-DECYL PHTHALATE		E														
DI-ISO-PROPANOLAMINE	E	E														
DI-ISO-PROPYL ETHER	F	E		X		X				X						E
DI-ISO-PROPYL KETONE	G	C	E	X		X	X	X		X		E		X	X	E
DI-P-MENTHA-1,8-DIENE		G														
DIACETONE ALCOHOL	E	E	X	X		X	X	X		X		E	E	X	X	C
DIACETYLMETHANE		E														
DIALLYLPHTHALATE		G														
DIAMMONIUM PHOSPHATE									E							
DIAMYL NAPHTHALENE	E			X		X				X					F	E
DIAMYLAMINE	E	E		G		F				G						
DIAMYLENE	X	G		X		X				X					E	E
DIAMYLPHENOL	X	E		X		X				X					E	E
DIBENZYL ETHER	E	C	X	X		X	X	X		X		E	E	G	X	E
DIBROMOBENZENE	X			X		X				X			G		E	E

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

CHEMICAL OR MATERIAL CONVEYED	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE
DIBROMOMETHANE		C														
DIBUTYL ETHER	G	E	C	X		X	X	X		X		E	E	C	C	E
DIBUTYL PHTHALATE	C	C	C	X	E	X	X	X	E	X		E	E	X	C	E
DIBUTYL SEBACATE	E	G	G	X		X	X	X		X		E	E	X	F	E
DIBUTYLAMINE	X	E	X	X		X	X	X		X		E	E	X	X	
DICALCIUM PHOSPHATE	E			E		E				E					E	E
DICHLORO ETHYLENE					X				C		X			C		
DICHLOROACETIC ACID	F	G		X		G				X					X	E
DICHLOROBENZENE	X	X	X	X	X	X	X	X	E	X	X	G	E	X	E	G
DICHLOROBUTANE	X	C	C	C		C	C	G		X			E	X	E	E
DICHLORODIFLUOROMETHANE	X			X		X				X					G	
DICHLOROETHANE	X	C		X		X				X					E	E
DICHLOROETHYL ETHER	X	G		X		X				X						E
DICHLOROHEXANE	X	C		X		X				X			E		E	E
DICHLOROMETHANE	X	C		X		X				X			E		E	E
DICHLOROPENTANE	X	C		X		X				X			E		E	E
DICHLOROPROPANE	X	C		X		X				X		E	E		E	E
DICHLOROPROPENE												E	E		E	E
DICHLOROTOLUENE		X														
DIESEL OIL	X		X	C	C	X	C	E	E	X	X	E	E	C	E	C
DIETHANOL AMINE	E	E		F	C	G				G			E			
DIETHLBENZINE	X	C	X	X		X	X	X		X			E	X	E	E
DIETHYL ETHER	X	E	X	X		X	C	X	G	X		G		G	X	E
DIETHYL KETONE	G	C		X		F				X					X	E
DIETHYL OXALATE	E	E		X		E				E						E
DIETHYL PHTHALATE	E	G	G	X	E	X	X		E	X		E	E		F	E
DIETHYL SEBACATE	E	G	C	X	G	X	X	X		X	E			X	E	
DIETHYL SULFATE		E														
DIETHYLAMINE	E	E	G	C		G	C	C		G		E	E	C	X	C
DIETHYLENE GLYCOL	E	E	E	E		E	E	E		E			E	X	E	C
DIETHYLENE OXIDE		G														
DIETHYLENETRIAMINE	E	E		F		G				G			E			
DIETHYLTRIAMINE	E	E		F		G				G						
DIHYDROXY DIETHYL ETHER		E														
DIHYDROXY SUCCINIC ACID		E														
DIHYDROXYDIETHYL ETHER	E			E		E				E					E	
DIISOBUTYL KETONE	G		G	X		X	X	X		X			E		X	E
DIISODECTYL PHTHALATE	E			X		X				X			E		F	E
DIISOOCTYL ADIPATE	E			X		X				X			E		F	E
DIISOOCTYL PHTHALATE	E			X		X				X			E		F	E
DIMETHYL CARBINOL		E											E			
DIMETHYL KETONE		E											E			
DIMETHYL PHTHALATE	G	E	G	X		X	X	X		X		E	E		G	E
DIMETHYL SULFATE		E														
DIMETHYL SULFIDE		G														
DIMETHYL-3-PENTANONE		C														
DIMETHYL-4-HEPTANONE		C														
DIMETHYLAMINE		E										E	E			E
DIMETHYLANILINE	C	C	G	X			C	C		C		E	G			

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:

E = EXCELLENT

G = GOOD

F = FAIR

C = CONDITIONAL

X = UNSATISFACTORY

BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

ENVIROFLEX®

Email: sales@enviroflexpumps.com

CHEMICAL OR MATERIAL CONVEYED

CHEMICAL OR MATERIAL CONVEYED	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE	KEY:
																	E = EXCELLENT
																	G = GOOD
																	F = FAIR
																	C = CONDITIONAL
																	X = UNSATISFACTORY
																	BLANK = NO DATA
ETHYLAMINE	G	E		F		F				F			E				
ETHYLENE CHLOROHYDRIN	G		C	G	X	G	C	X		G	X	E	E	X	E	E	
ETHYLENE DIAMINE	E	G	E	F		G	E	E		G		E	G	X	X	E	
ETHYLENE DIBROMIDE	X	C	C	X		X	X	X		X			G	X	G	G	
ETHYLENE DICHLORIDE	X	C	X	X	X	X	X	X	E	X	X	E	G	X	G	G	
ETHYLENE G MONOETHYL E ACETATE										E							
ETHYLENE G MONOBUTYL ETHER																	E
ETHYLENE G MONOETHYL ETHER																	E
ETHYLENE G MONOHEXYL ETHER																	E
ETHYLENE GLYCOL	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	C
ETHYLENE OXIDE	C		C	X	E	X	X	X	E	X		X		X	X		
FATTY ACIDS	X	G	X	X		X	C	C	E	X	X	E	E		E	E	
FERRIC BROMADE	E			E		E				E			E		E	E	
FERRIC CHLORIDE	E	E	E	E	C	E	G	E	X	E		E	E	E	E	E	
FERRIC NITRATE	E	E	E	E		E	E	E	E	E		E	E	E	E	E	
FERRIC SULFATE	E	E	E	E		E	E	E	X	E		E	E		E	E	
FERROUS ACETATE	G			X		X				X						X	E
FERROUS CHLORIDE	E		E	E	E	E	E	E	E	E		E	E	E	E	E	
FERROUS SULFATE	E	E	E	E	E	E	E	G	E	E		E	E	E	E	E	
FLUOBORIC ACID	E	E	E	E		E	C	C		G		E	C		C	C	
FLUORINE	C		X			X	X	X	X	X	X	X	X	X	G	X	
FLUOSILICIC ACID	E	E	E	E	C	E	C	C		C		E	C		C	C	
FORMALDEHYDE	E	E	G	C	C	G	C	X	E	C	E	E	E	X	X	E	
FORMALIN	E	E		E		G				G					E	E	
FORMIC ACID	E	E	E	F	C	G	C	X	X	G	E	E	E	X	X	C	
FREON 502			E				E		E		X	E					
FREON 113			C	E	E	C	E	E		G	X	E			G		
FREON 12	X	E	X	X	G	X	G	G	E	X	X	X		G	G	C	
FREON 22	F	E		X	X	X	X	X	X	X	X	X		X	X	C	
FUEL A (ASTM)	X		X	X		X	G	E		X					E	G	
FUEL B (ASTM)	X		X	X		X	F	E		X					E	G	
FUEL OIL	X	E	X	C	X	X	G	E	E	X		E	E	X	E	C	
FURAN	X	E	C	X		X	X	X		X							
FURFURAL	E	E	C	X		X	X	X		X	E	E	E		X	E	
FURFURAN		E	C	X		X	X	X		X		E					
FURFURYL ALCOHOL	F	E	G	X		X	X	X	E	X	E	G	E	X	G	E	
GALLIC ACID	G	E	G	C		E	X	C		C		E	E	X	C	C	
GALLOTANNIC ACID		E															
GAS, COAL									E		X						
GAS, HIGH OCTANE			X		E		X	G	E		X	E	C	C			
GASOLINE	X	G	X	X	E	X	X	E	E	X		E	E	G	E	E	
GLACIAL ACRYLIC ACID																	E
GLUCONIC ACID	F	E		G		X				X			E			E	
GLUCOSE	E		G	E		E	G	G	G	E		G	E	X	E	E	
GLYCERINE	E	E	E	E	E	E	E	E	E	E	X	E		X	E	C	
GLYCEROL	E	E	E	E		E	E	E	E	E		E		X	E		
GLYCOGENIC ACID		E															
GLYCOLS	E	E	E	E	G	E	E	E	E	E	G	E	E	X	E	E	
GLYCONIC ACID		E															

ENVIROFLEX®

Pump Point, Ascot Drive, Derby, DE24 8GZ

Email: sales@enviroflexpumps.com

CHEMICAL OR MATERIAL CONVEYED

CHEMICAL OR MATERIAL CONVEYED	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE	KEY:
																	E = EXCELLENT
																	G = GOOD
																	F = FAIR
																	C = CONDITIONAL
																	X = UNSATISFACTORY
																	BLANK = NO DATA
CHEMICAL OR MATERIAL CONVEYED																	
GLYCYL ALCOHOL			E														
GREASE	X			X	X	E	X	X	E	E	X	X	E	E	E	E	G
GREEN SULFATE LIQUOR	E	G	E	E		E	G	G	C	E			E	E		E	E
HALON 1211							E	E									
HELIUM	E			E	E	G	E	E	E	E			G		G	E	
HEPTALDEHYDE		G															
HEPTANAL	E	G		X		X				X				E			E
HEPTANE	X	E	X	X	G	X	G	E	E	X			E	E	G	E	G
HEPTANE CARBOXYLIC ACID		E															
HEPTANOIC ACID		E															
HEPTANONE		C															
HEXADECANOIC ACID		E															
HEXALDEHYDE	G		E	C		X	E	X		X			E	E	G	X	E
HEXANE	X	G	X	X	X	X	C	C	E	X			E	G	G	E	G
HEXANOL	E	E		E		E				E						G	E
HEXENE	X	E	X	G		X	G	G		X			E			E	E
HEXYL ALCOHOL	C	E	C	C		E	G	E		E			E	E	X	G	E
HEXYL METHYL KETONE	G			X		X				X						X	E
HEXYLAMINE	E	G		F		G				G							
HEXYLENE GLYCOL	E	E		E		E				E						E	
HISTOWAX		E															
HYDRAULIC & MOTOR OIL	X	E	X	G	E	X	C	E	E	X	X		E	E	E	E	E
HYDRAZINE	E	C	X	E	G	X	G	X	E				X		X		
HYDROBROMIC ACID	E	E	E	E		E	X	X	X	X			E	G	X	C	C
HYDROCHLORIC ACID	F	E	X	X	C	E	X	X	X	X			E	E	C	E	E
HYDROCYANIC ACID	E	C	C	C	X	X	E	C	G				E	E	E		
HYDROFLUORIC ACID	E	E	X	E	X	X	X	X	X	X	X	X	E	E	X	G	C
HYDROFLUOSILICIC ACID	E	E	E	E	C	X	C		E				E	C	G		
HYDROGEN CHLORIDE ANHYDROUS		E															
HYDROGEN DIOXIDE (11%)		E															
HYDROGEN GAS	E	E	E	G	E	G	E	E	E	G			E	E	E	C	E
HYDROGEN PEROXIDE OVER 10%	X	E	X	X		X	X	X	X	X			E	G		E	C
HYDROGEN PEROXIDE 10%	F	E	F	F		X	F	X	X	X			E	G		E	C
HYDROGEN SULFIDE (WET)	E	G	E	X	E	X	C	X	X	X			E	E	X	X	E
YDROXY BENZENE		E															
HYDROXYISOBUTYRONITRILE		E															
HYDROXYTOLUENE		E															
HYVAR XL			E														
IMINODI-2-PROPANOL		E															
IMINODIETHANOL		E															
IODINE	C	E	C	E		C	X	C		C				G		C	C
IODINE PENTAFLUORIDE	X		X	X		X	X	X		X				C	X	X	
ODOFORM			X			X	X	E		X							
ISO-BUTANAL		G															
ISO-BUTYLAMINE		G															
ISO-BUTYLBROMIDE		C															
ISO-BUTYLCARBINOL		E															
ISO-OCTANE		E															

ENVIROFLEX®

Email: sales@enviroflexpumps.com

CHEMICAL OR MATERIAL CONVEYED

[illegible]

ENVIROFLEX®

Email: sales@enviroflexpumps.com

CHEMICAL OR MATERIAL CONVEYED

CHEMICAL OR MATERIAL CONVEYED	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE	KEY:
																	E = EXCELLENT
																	G = GOOD
																	F = FAIR
																	C = CONDITIONAL
																	X = UNSATISFACTORY
																	BLANK = NO DATA
METHYL ACETATE	G	E	E	X		X	X	X	E	X		E	E	X	X	E	
METHYL ACETOACETATE	G	E	G	X		X	X	X		X				X	X	E	
METHYL ACETONE	G	E		X		F				X			E		X	E	
METHYL ACETYLENE PROPADIENE			G				E	E		G							
METHYL ALCOHOL	E	E	E	E		E	E	E	E	E		E	E	X	E		
METHYL ALLYL ALCOHOL		E															
METHYL ALLYL CHLORIDE	F	C		X		X				X					F	G	
METHYL AMYL CARBINOL	E			E		E				E					X	E	
METHYL BENZENE	X	C		X		X				X					E	E	
METHYL BROMIDE	X		X	X		X	X	C	E	X	X	E	G		E	G	
METHYL BUTANE		E															
METHYL BUTANE ALCOHOL		E															
METHYL BUTYL KETONE	G		E	X		X	X	X		X			E	X	X		
METHYL CARBITOL	F	E		X		X				X						E	
METHYL CELLOSOLVE	E	E	G	X		X	C	C		X		E	E	X	X		
METHYL CHLORIDE	C	X	X	X	X	X	X	X	X	X	X	E		X	E	G	
METHYL CYANIDE		E															
METHYL EHTYL KETONE	G	C	E	X	C	X	X	X	E	X	X	E	E	X	X	E	
METHYL HEXANOL	E			E		E				E			E		F	E	
METHYL METHACRYLATE	X	C	C	X		X	X	X	C	X	C	E	G		X	G	
METHYL NORMAL AMYL KETONE	G			X		X				X					X	E	
METHYL PROPYL ETHER	G			X		X				X						E	
METHYL SALICYLATE	G		G	X		C	X	X		C		E			C		
METHYL STYRENE		C															
METHYL SULFIDE		C															
METHYL TERTIARY BUTYL ETHER	G	X					X	X		X		G	G		X		
METHYL 1-2,4-PENTANEDIOL		E															
METHYL-ISO-AMYL-KETONE		C															
METHYL-L-PROPANOL		E															
METHYL-2-BUTANOL	E	E		E		E				E					F	E	
METHYL-2-BUTANONE	G	G		X		X				X					X	E	
METHYL-2-HEXANONE	G	C		X		X				X					X	E	
METHYL-2-PENTANOL		E															
METHYL-2-PENTANONE		C															
METHYL-2-PROPEN-L-OL		E															
METHYL-3-PENTEN-1-ONE		C															
METHYL-4-ISOPROPYL BENZENE		C															
METHYLALLYL ACETATE	G			X		X				X					X	E	
METHYLYAMYL ALCOHOL	E	E		E		E				E					X	E	
METHYLCYCLOHEXANE	X	G		X		X				X					G	G	
METHYLENE BROMIDE		C															
METHYLENE CHLORIDE													G				
METHYLETHYL KETONE	G	C	E	X	C	X	X	X	E	X	X	E	E	X	X	E	
METHYLHEXYL KETONEG	C		X		X				X						X	E	
METHYLISOBUTYL CARBINOL	E	E	E	C		G	G	G		G					C	C	
METHYLISOBUTYL KETONE	C	C	C	X	C	X	X	X	E	X	X	E	E	X	X	E	
METHYLISOPROPYL KETONE	G	G	X	X		X	X	X	E	X		E		X	X	E	
METHYLLACTONITRILE		E															
METHYLPHENOL		E															

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SANTOPRENE	SBR	TEFLON	UHMW	URETHANE	VITON	XLPE
METHYLPROPYL CARBINOL		E														
METHYLPROPYL KETONE	G	G		X		X				X					X	E
MINERAL OIL	X	E	X	F	E	X	C	E	E	X	X	E	E	E	E	E
MINERAL SPIRITS	X		X	X		X	F	E		X			E		E	E
MOBILE HFA			X					E	E			E				
MOLTEN SULFUR	G			F		X				X			X		G	X
MONO-CHLOROACETIC ACID	F	E		X		G				X					C	E
MONOBUTYL ETHER	F			X		X				X					X	E
MONOCHLOROBENZENE	X		X	X	C	X	X	X	G	X	X	E	G	X	E	G
MONOCHLORODIFLUOROMETHANE	F			X		X				X					X	C
MONOETHANOL AMINE	E		E	X		E	X	X		X			E	X	X	E
MONOETHYL AMINE	G			F		F				F					C	C
MONOETHYLAMINE		E										E				E
MORPHOLINE			X					X	X			E				
MOTOR OIL, 40W		E											E			
MTBE	G	X					X	X		X		G	G		X	
MURIATIC ACID	F	E	F	X		E	X	X		X			E		E	E
N-BUTANAL		G														
N-BUTYLAMINE	X	G	X	X		X	X	C		X				X	X	
N-BUTYLBENZENE	X	C		X		X				X					E	E
N-BUTYLBROMIDE	X	C		X		X				X					G	G
N-BUTYLBUTYRATE	F	C		X		X				X					X	G
N-BUTYLCARBINOL		E														
N-NONYL ALCOHOL		E														
N-OCTANE	X	E	X	X		X	G	G		X				X	E	G
N-SERV (75% XYLENE)									E			E			E	C
NA-K			X					X				X				
NAPHTHA	X	E	X		E	X	X	C	E	X	X	E	E	E	E	E
NAPHTHALENE	F	E	X	X	C	X	X	X	E	X	X	E	E	C	C	E
NAPHTHENIC ACIDS		E	X	X		X	X	G		X		E			E	
NATURAL GAS	X	X	X	X	X	X	X	X	X	X	X	X		X	X	X
NEOHEXANE	X	G		X		X				X					E	E
NEON GAS	E		E	E		E	E	E	E	E	E	E		E	E	
NEU-TRI	X			X		X				X					E	E
NICKEL ACETATE	E		E	X		E	G	G		X		E	E	X	X	E
NICKEL CHLORIDE	E	E	E	E		E	G	E	X	E		E	E	C	E	E
NICKEL NITRATE	E	E	E	E		E	E			E			E		E	E
NICKEL SULFATE	E	E	E	E		E	E	E	E	E		E	E		E	E
NIETYLENE						E										
NITRIC ACID, CONC (16N)	C	X	X	G	C	X	X	X	X	X	X	E	E	X	C	G
NITRIC ACID, RED FUMING	G	X	X	X	C	X	X	X	X	X	X	E	X	X	X	X
NITRIC ACID, 10%	G		C	X	C	X	X	X	X	X	E	E	E	X	X	C
NITRIC ACID, 13N		E										E				
NITRIC ACID, 13N +5%		E										E				
NITRIC ACID, 20%	G		G	X	F	X	X	X		X		E	E		C	E
NITRIC ACID, 30%	F		C	X	X	X	X	X	X	X		G	E	C	C	E
NITRIC ACID, 30% - 70%	F		F	F		X	X	X		X			E		C	G
NITRILOTRIETHANOL		E														
NITROBENZENE	F	C	X	X	C	X	X	X	E	X	C	E	E	X	G	E

ENVIROFLEX®

Pump Point, Ascot Drive, Derby, DE24 8GZ

Email: sales@enviroflexpumps.com

CHEMICAL OR MATERIAL CONVEYED

CHEMICAL OR MATERIAL CONVEYED	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE	KEY:
																	E = EXCELLENT
																	G = GOOD
																	F = FAIR
																	C = CONDITIONAL
X = UNSATISFACTORY																	
BLANK = NO DATA																	
NITROETHANE	G	E	G	G		G	C	X		G		E	E	X	X	E	
NITROGEN	E	E	E	E		E	E	E	G	E		E	E	E	E	E	
NITROMETHANE	G		G	C		G	C	X		C		E	E	X	X	E	
NITROUS OXIDE GAS									X			E	E				
NONANOIC ACID		E															
NONANOL		E															
NUTO H			X					E	E			E					
NYVAC LIGHT			E					X	E			E					
OCTANOIC ACID		E															
OCTANOL	E	E		G		G				G			E		G	E	
OCTYL ACETATE	G	C		X		X				X			E		X	E	
OCTYL ALCOHOL	E	E	C	E		E	G	G		E		E	E	X	E	E	
OCTYL ALDEHYDE	E	E		X		X				X					X	E	
OCTYL AMINE	E	G		F		G				G					C	C	
OCTYL CARBINOL	E	E		E		E				E					G	E	
OCTYLENE GLYCOL	E			E		E				E					E	C	
OIL-PETROLEUM	X		X	F		X	G	E		X			E		E	E	
OLEIC ACID	G	E	X	X	E	X	X	C	E	X		E	E	G	G	E	
OLEUM (FUMING SULFURIC ACID)	X		X	X	X	X	X	C	E	X		E	X	C	X	X	
OLIVE OIL	E	G	E	F		X	E	E		X		E	G	E	E	C	
ORTHO-DICHLOROBENZENE	X		X	X		X	X	X		X		G		X	E	G	
ORTHO-DICHLOROBENZOL	X			X		X				X					G	G	
ORTHOXYLENE	X			X		X				X					E	E	
OXALIC ACID	E	E	E	X		X	X	X	X	X	E	E	E	E	C	C	
OXYDIETHANOL		E															
OZONE	G	E	E	G		X	C	X	X	X		E	C	G	C	C	
P-CYMENE	X	X	X	X		X	X	X		X		E	E	X	E	E	
PAINT THINNER	X		X	X		X	X	X		X	X	E	E	X	G		
PALMITIC ACID	E	E	C	C	E	X	C	E	X	X	E	E	E	E	C	C	
PAPERMAKERS ALUM	E		E	E		E	E	E		E			G		E	E	
PARA-DICHLOROBENZENE	X		X	X		X	X	X		X				X	E	G	
PARAFFIN WAX	X	E	X	X		X	G	E		X			E		E	X	
PARALDEHYDE	E					F									X	E	
PARAXYLENE	X			X		X				X					E	E	
PCB												E			E		
PELARGONIC ALCOHOL	E	E		X		X				X						E	
PENTACHLOROETHANE	X			X		X				X					E	E	
PENTADIONE		G															
PENTAMETHYLENE		G															
PENTANE	X	E	X	F		X	G	E		X			G	X	E	G	
PENTANOL		E															
PENTANONE	G	C		X		X				X					X	E	
PENTASOL	E			E		E	E			E					E	E	
PENTYL ACETATE		C															
PENTYL ALCOHOL		E															
PENTYL BROMIDE		C															
PENTYL CHLORIDE		C															
PENTYL ETHER		E															
PENTYLAMINE		G															

ENVIROFLEX®

Email: sales@enviroflexpumps.com

CHEMICAL OR MATERIAL CONVEYED

CHEMICAL OR MATERIAL CONVEYED	KEY: E = EXCELLENT G = GOOD F = FAIR C = CONDITIONAL X = UNSATISFACTORY BLANK = NO DATA																
	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE	
PERCHLORIC ACID-2N	G		C	G	X	X	C	X	C	X	X	E		X	E	E	
PERCHLOROETHYLENE	X	C	X	X	X	X	X	X	X	X	X	E	G	X	E	G	
PERCHLOROMETHANE		C															
PETROLEUM CRUDE	X	E	X	X		X	G	E		X			E	E	E	E	
PETROLEUM ETHER	X	E	X	X		X		G	E	X		E			E	E	
PETROLEUM OILS	X		X	X		X	G	X	G	X		E	E		E	E	
PHENBO													E	X			
PHENOL	E	E	X	X	X	X	X	X	X	X	X	E	E	X	E	E	
PHENOLSULFONIC ACID	F	E		X		X				X			G		X	G	
PHENYLAMINE		G															
PHENYLBROMIDE		X															
PHENYLBUTANE		C															
PHENYLCHLORIDE	X	X		X		X				X					E	E	
PHENYLETHYLENE		C															
PHENYLMETHANE		C															
PHENYLMETHANOL		X															
PHENYLMETHYL ACETATE		G															
PHOSPAHTE ESTERS			E		X			X	E		E	E		X			
PHOSPHORIC ACID 10%	E	E	X	E		E	X	X	X	E		E	E		E	E	
PHOSPHORIC ACID 10% - 85%	G	E	X	E		G	X	X	C	X	E	E	E	X	E	E	
PHOSPHORUS TRICHLORIDE	E	X	E	X		X	X	X		X		E			E		
PICRIC ACID, H2O SOLUTION		G	X	G	C	G	C	X	X	G	X	E		X	E		
PINE OIL	X	G	X	X		X	X	X		X		E	E		E	E	
PINENE	X	G	X	X		X	F	G		X		E	E	G	E	E	
POLY CHLORINATED BIPHENOL												E			E		
POLYETHYLENE GLYCOL E-400	E	E		E		E				E					E		
POLYOL ESTER	X		X			X	X	G							G		
POLYPROPYLENE GLYCOL	E			E		E				E					E		
POTASSIUM ACETATE	G	E	E	X		X	G	G		X		E	E	X	X	E	
POTASSIUM BISULFATE	E	E		E		E				E			E		E	E	
POTASSIUM BISULFITE	E	E		E		E				E			E		E		
POTASSIUM CARBONATE	E	E	E	E		E	E		G	E			E		E	E	
POTASSIUM CHLORIDE	E	E	E	E		E	E	E	E	E		E	E	E	E	E	
POTASSIUM CHROMATE	E	E		F									G			G	
POTASSIUM CYANIDE	E	E	E	E		E	E	E	E	E		E	E	E	E	E	
POTASSIUM DICHROMATE	E	E	E	F	C	G	E	E		G		E	G	G	E	G	
POTASSIUM HYDRATE	E			G		E				G					F	E	
POTASSIUM HYDROXIDE	E	E	E	G	G	E	C	X	C	G		E	G	C	X	E	
POTASSIUM NITRATE	E	E	E	E		E	E	E	E	E		E	E	E	E	E	
POTASSIUM PERMANGANATE, 5%					X								E				
POTASSIUM SILICATE	E	E		E		E				E					E	E	
POTASSIUM SULFATE	E	E	E	E		E	E	E	E	E		E	E	G	E	E	
POTASSIUM SULFIDE		E											E				
POTASSIUM SULFITE	E	E	E	E		E	E			E					E	E	
PRESTONE ANTIFREEZE			E				E	E							E		
PRODUCER GAS	X		X	G		X	G	E		E		E			E		
PROPANE	X	E	X	G		X	C	E	E	X		E		E	E	E	
PROPANEDIOL	E	E		E		E				E					E		
PROPANETRIOL		E															

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE
PROPANOL	E	E		E		E				E					F	E
PROPANOLAMINE		E														
PROPANONE		E														
PROPEN-L-OL		E														
PROPENEDIAMINE		E														
PROPENENITRILE		E														
PROPENYL ALCOHOL		E														
PROPENYLANISOLE		X														
PROPIONIC ACID			E					X								E
PROPIONITRILE			X				G	E							E	
PROPYL ACETATE	G	G	G	X		X	X	X		X			E	X	X	E
PROPYL ALCOHOL	E	E	E	E		E	E	E		E			E	C	E	E
PROPYL ALDEHYDE	E					F							E		X	E
PROPYL BENZENE		C														
PROPYL CHLORIDE	F	C		X		X				X			E		G	G
PROPYL ETHER		E														
PROPYL NITRATE	G	G	G	X		X	X	X		X					X	
PROPYLENE	X	E	X	X		X	X	X		X					X	E
PROPYLENE DIAMINE	E			F		G				G						
PROPYLENE GLYCOL	E			E		E				E		E	E	E	E	
PYDRAUL, 'E' SERIES		G	E	X	E	X	X	X	E	X		E	E		X	E
PYDRAULIC 'C'			X		E		X	X				E			E	
QUINTOLUBRIC 822 SERIES	X		X			X	X	G							G	
RED OIL	X	E	X	G		X	G	E		X		E		G	E	
REFRIGERANT 11			X				X	G							G	
REFRIGERANT 12			X				G	E							G	
REFRIGERANT 22			X				G	X							G	
RESORCINOL					X			X	X		X	E		X		
SAE NO.10 OIL				X	E		C	G	E		X	E		E	X	
SAL AMMONIAC	E	E	E	E		E	E	E		E				E	E	
SEA WATER	E		E	E	E	E	G	E	E	E	E	E	E	E	E	E
SEWAGE	F	E	F	E		F	E	E	E	F		E	E	X	C	E
SILICATE ESTERS	X		X	E		X	E	G	E	X		E			E	
SILICATE OF SODA	E	E		E		E				E					E	E
SILICONE GREASE	E	E	E	E	E	E	E	E		E		E			E	
SILICONE OIL	E	E	E	E		E	E	E		E			E		E	
SILVER NITRATE	E	E	E	E		E	E	G		E		E	E	E	E	E
SKYDROL 500 TYPE 2			E	X			X	X				E			X	
SKYDROL 500B	G	G	E	X	E		X		E		E	E		C	X	
SKYDROL 500C	G	G		X	E		X					E			X	
SKYDROL 7000 TYPE 2			E				X	X				E			G	
SOAP SOLUTIONS	E	E	E	E	E	G	G	E	E	E	E	E		C	E	E
SODA ASH	E	E	E	E		E	E	E	E	E		E	E		E	E
SODA LIME	E			G		E				G			E		F	E
SODA NITER	E	E		E		E				E					E	E
SODA, CAUSTIC	E			E		G				G			E		F	E
SODIUM ACETATE	G	E	E	X		X	G	G		X		E	E	E	X	E
SODIUM ALUMINATE	E	E		E		E				E			E		E	E
SODIUM BICARBONATE	E		E	E		E	E	E		E		E	E		E	

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

	BUTYL	CPE	EPDM	HYPALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SANTOPRENE	SBR	TEFLON	UHMW	URETHANE	VITON	XLPE
SODIUM BISULFATE	F	E	E	E		F	E	E	E	F		E	E		C	E
SODIUM BISULFITE	E	E	E	E		E	E	E		E		E	E		E	C
SODIUM BORATE	E	E	E	E		E	E	E		E		E	E		E	E
SODIUM CARBONATE 10% - 15%	E	E	E	E		E	E	E		E			E		E	E
SODIUM CHLORIDE	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E	E
SODIUM CYANIDE	E	E	E	E		E	E	E	E	E		E	E		C	E
SODIUM DICHROMATE	E	E	E	F	X	C	C	C		C			E		C	G
SODIUM HYDRATE	E			G		E				G					F	E
SODIUM HYDROCHLORITE	G		G	F		X	X	X		X					G	G
SODIUM HYDROXIDE (CAUSTIC SODA)	E	E	E	G	G	E	G	X	C	G		E	E	G	G	E
SODIUM HYPOCHLORITE	G	E	G	F	E	X	X	G	X	X	E	E	E	X	E	G
SODIUM METAPHOSPHATE	E	E	E	G		E	G	E		E		E	E		E	E
SODIUM NITRATE	E	E	E	E		E	G	G	E	E		E	E	X	C	E
SODIUM PERBORATE	E		E	G		G	G	G	E	G		E	E		E	E
SODIUM PEROXIDE	E	G	E	G	C	G	G	G		G		E	E	X	E	E
SODIUM PHOSPHATE	E	E	E	E		E	G	E	E	E		G	E	E	E	E
SODIUM SILICATE	E	E	E	E		E	E	E	E	E		E	E		E	E
SODIUM SULFATE	E	E	E	E		E	E	E	E	E		E	E		E	E
SODIUM SULFIDE	E	E	E	E		E	E	E	E	E				E	E	E
SODIUM SULFITE	E	E	E	E		E	E	E		E			E	E	E	E
SODIUM THIOSULFATE	E	E	E	E		E	E	G	E	E		E	E	E	E	E
SOYBEAN OIL	E		C	G	C	X	G	E	E	X		E	E	G	E	E
STANNIC CHLORIDE	E	E	E	E		E	X	E	E	E		E	E			E
STANNIC SULFIDE	E			E		E				E						E
STANNOUS CHLORIDE	E	E	E	E	C	E	E	E		E		E	E		C	E
STANNOUS SULFIDE	E			E		E				E						E
STEAM, BELOW 350° F	G	X	E	X	C	X	X	X	X	X		E	X	X	X	X
STEARIC ACID	G	E	G	X	C	X	G	G	E	X	E	E	E	E	C	E
STODDARD SOLVENT	X	E	X	X		X	G	E		X		E	E	E	E	E
STYRENE	X	C	X	X	X	X	X	X	E	X		E	G	E	G	G
SULFAMIC ACID	E	E	E	G		G	G	G		G					C	C
SULFUR	F		F	F		X	X	X		X		E	E		G	X
SULFUR CHLORIDE	X		X	G		X	C	C	G	X		E	E		E	E
SULFUR DIOXIDE	G		G	G	C	C	X	X	X	C		E	G		C	C
SULFUR TRIOXIDE, DRY	G	X	G	X		G	X	X	X	G		E	X		E	G
SULFURIC ACID 60% (200F)		G											X			X
SULFURIC ACID, CONC. TO 98%	X	X	X	E	C	X	X	X	X	X		C	E	X	E	E
SULFURIC ACID, FUMING	X	X	X	X	X	X	X	X		X		E	X		X	X
SULFURIC ACID, 25%	E		E	X	X	G	X	X	X	X		E	E	X	F	E
SULFURIC ACID, 25% - 50%	E	E	E	X	X	G	X	X	X	X		E	E	X	G	E
SULFURIC ACID, 50% - 96%	X		X	G	X	X	X	X	X	X		E	E	X	E	E
SULFUROUS ACID, 10%	E	E	G	E	G	E	X	X		G		E	E		C	E
SULFUROUS ACID, 10% - 85%	E	E	G	E	G	E	X	X		X		E	E		C	E
SUTAN												E			F	E
T-BUTYLAMINE			G	X												
TALL OIL	X		X	X		X	G	E		X			E		E	C
TALLOW	X		X	X		X	G	E		X			E		C	C
TANNIC ACID	E	E	E	E	E	E	G	E	X	F	E	E	E	C	C	C
TAR	X		X	X		X	G	X	X	X		E	X		E	X

CHEMICAL COMPATIBILITY CHART

Enviroflex Limited

Pump Point, Ascot Drive, Derby, DE24 8GZ

Tel: +44 (0) 1332 913200 Fax: +44 (0) 1332 653 500

Email: sales@enviroflexpumps.com



KEY:
E = EXCELLENT
G = GOOD
F = FAIR
C = CONDITIONAL
X = UNSATISFACTORY
BLANK = NO DATA

CHEMICAL OR MATERIAL CONVEYED

	BUTYL	CPE	EPDM	HYALON	HYTREL	NATURAL	NEOPRENE	NITRILE	NYLON	SBR	SANTOPRENE	TEFLON	UHMW	URETHANE	VITON	XLPE
TAR BITUMINOUS	X		X	X		X	C	G		X		E			E	
TARTARIC ACID	E	E	G	E	C	C	G	E	X	X	E	E	E	C	C	C
TELONE 2																E
TERPINOL	C	E	C	X		X	X	G		X		E	G	G	E	G
TERTIARY BUTYL ALCOHOL	E	G	G	E		E	G	G		E		E		X	E	E
TERTIARY BUTYL AMINE			G	X												
TERTIARY BUTYL MERCAPTAN	X		X	X		X	X	X		X		E			E	
TETRACHLOROBENZENE	X			X		X				X					G	G
TETRACHLOROMETHANE	X	C		X		X				X					E	E
TETRACHLOROETHYLENE	X	X	X	X		X	X	X	C	X			E	X	E	E
TETRACHLORONAPHTHALENE	X			X		X				X					G	G
TETRAETHYLENE GLYCOL	E			E		E				E					E	
TETRAETHYLORTHOSILICATE		E			G			X								
TETRAHYDROFURAN	X	X	X	X	G	X	X		C	X	X			X	X	C
THF									C							C
TIN CHLORIDE	E			E		E		G		E			E			E
TITANIUM TETRACHLORIDE	X	X	X	X	C	X	X	X		X			G	X	E	
TOLUENE	E	X	X	X		X	X		E	X	X	E	E	X	E	G
TOLUIDINE		C														
TOLUOL		C														
TRANSFORMER OIL	X	E	X	C		X	G	E		X		E	E	E	E	
TRANSMISSION 'A' OIL	X	E	X	X		X	G	E	E	X		E		E	E	F
TRI (2-HYDROXYETHYL) AMINE		E														
TRIBUTYL PHOSPHATE	E	C	G	X		X	X	X	E	X		E	E	X	X	E
TRIBUTYLAMINE	E	E		F		G	G			G						
TRICHLOROACETIC ACID	G		G	X		C	X	G		G		E	E	X	C	E
TRICHLOROBENZENE	X	X		X		X				X					G	G
TRICHLOROETHANE	X	X	X	X		X	X	X		X		E		X	E	G
TRICHLOROETHYLENE	X	X	X	X	C	X	X	X	E	X		X	G	X	E	G
TRICHLOROMETHANE		X														
TRICHLOROTOLUENE		X														
TRICRESYL PHOSPHATE	E	E	X	X		X	X	X		X		E	E	X	G	E
TRIETHANOLAMINE	E	E	G	G	X	E	G	C		X		E	E	X	X	E
TRIETHYLAMINE	E	E		F		G				G						
TRIETHYLENE GLYCOL	E	E		E		E				E					E	
TRIHYDROXYBENZOIC ACID		E														
TRIMETHYL PENTANES (MIXED)		E														
TRIMETHYL PENTENE		E														
TRIMETHYLAMINE		E										E	E			E
TRISODIUM PHOSPHATE	E	E	E	E	E	E	E	E	E	E		E		E	E	E
TRITOYL PHOSPHATE		E														
TUNG OIL							G						E			
TUNG OIL (CHINA OIL)	C		X	C	C	X	G	E		X		E	E	C	E	E
TURPENTINEX	X	G	X	X		X	X	X	E	X	X	E	G	E	E	G
UDMH			E	E		E	G	G		E					X	
UNDECYL ALCOHOL		E														
UREA	E	E					E		E			E	E	E		E
URETHANE FORMULATIONS								E	E			E				
URIC ACID									E		E					

ENVIROFLEX®

Email: sales@enviroflexpumps.com

CHEMICAL OR MATERIAL CONVEYED

[illegible]